

DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
Lightfastness:	5	54004
Abrasion values:	Level:	
Dry	4 - 5	53339
Wet	3 - 4	
Perspiration	3 - 4	
Permanent folding behavior: 20.000 bucklings	passed	53340
Tensile strength: 20 N/mm	passed	53329

AMARETTINI 344

A rectangular brown leather tag with a green string tied through a hole at the top. The tag has a white dashed border and is set against a light green background.

Color: Amarettini 344
Collection: Rodeo
Thickness: 1,4 - 1,6 mm

SG-Test:	passed	
----------	--------	--

Burning behavior: EN1021 part I u. II	passed	
--	--------	--

Detaillied information about light fastness, abrasion values, skin tollernace and burning behaviour can be found at:
www.vegetable-tanned-leather.com/data-and-facts.html

Tested for
Heavy metals, chrome
(Conducted by the German Institute of Environment in Bremen, 2014/2015)

DATA SHEET



Results of the examination for chrome

Parameter	K 2300 FL-1 Ecopell 344 Amarettini KW 14 (mg/kg)	BG (mg/kg)	Requirements GOTs* (mg/kg)
chrome	<1	1	<1

* Global Organic Textile Standard, Version 4.0, requirements for ingredients and accessories

Results of the examination for heavy metals

Heavy metals	H 9379 FL-3 Ecopell 344 Amarettini KW 32 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)
Antimony	<0,5	0,5	1
Aluminium	70	10	500
Arsenic	<0,5	0,5	1
Lead	<0,5	0,5	1
Cadmium	<0,2	0,2	0,2
Chrome	17	1	50
Cobalt	<1	1	5
Mercury	<0,1	0,1	0,2
Nickel	<1	1	5
Titanium	<10	10	500
Zirconium	<5	5	500

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected