

DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
Lightfastness:	5-	54004
Abrasion values:	Level:	
Dry	5	53339
Wet	3-	
Perspiration	3-	
Permanent folding behavior: 20.000 bucklings	passed	53340
Tensile strength: 20 N/mm	passed	53329
Burning behavior: EN1021 part I u. II	passed	



Detailed information about light fastness, abrasion values, skin tolerance and burning behaviour can be found at:
www.vegetable-tanned-leather.com/data-and-facts.html

Tested for
Heavy metals
(Conducted by the German Institute of Environment in Bremen, 2015)

DATA SHEET



Results of the examination for heavy metals

Heavy metals	K 2263 FL I-1 Ecopell 838 Espresso KW 7 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)
Antimony	0,5	0,5	1
Aluminium	70	10	500
Arsenic	<0,5	0,5	1
Lead	<0,5	0,5	1
Cadmium	<0,2	0,2	0,2
Chrome	12	1	50
Cobalt	<1	1	5
Mercury	<0,1	0,1	0,2
Nickel	1	1	5
Titanium	<10	10	500
Zirconium	<5	5	500

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected