

DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN	INDIANSUMMER 101
Lightfastness:	2 - 3	54004	
Possible color change:			
Abrasion values:	Level:		
Dry	5	53339	
Wet	3		
Perspiration	3		
Permanent folding behavior: 20.000 bucklings	passed	53340	Color: Indiansummer 101 Collection: Velour Thickness: 1,4 - 1,6 mm
Tensile strength: 20 N/mm	passed	53329	
Burning behavior: EN1021 part I u. II	passed		
Detaillied information about light fastness, abrasion values, skin tollernace and burning behaviour can be found at: www.vegetable-tanned-leather.com/data-and-facts.html			Optional and only subject to availability. Please ask explicitly.
Tested for Heavy metals, aniline, (Conducted by the German Institute of Environment in Bremen, 2013)			

DATA SHEET



Results of the examination for aniline

Parameter	H 8235 FL-2 Ecopell 101 Indiansummer KW 45 (mg/kg)	NG (mg/kg)	Requirements IVN Leather (mg/kg)
Aniline	10	5	60*

* Sum limit for further amines going beyond European legislation
(2,4 Xylidine, N,N. Dimethylaniline, 5-Chlorine-o-toluidine, p-Phenylenediamine and Aniline)

Results of the examination for heavy metals

Heavy metals	K 2407 FL-4 Ecopell 229 Himbeer KW 40 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)
Antimony	<0,5	0,5	1
Aluminium	20	10	500
Arsenic	<0,5	0,5	1
Lead	<0,5	0,5	1
Cadmium	<0,2	0,2	0,2
Chrome	12	1	50
Cobalt	<1	1	5
Mercury	<0,1	0,1	0,2
Nickel	<1	1	5
Titanium	<10	10	500
Zirconium	<5	5	500

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected