

# DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
------------	--------	----------------

MISS PIGGY 226
----------------

Lightfastness:	2 - 3	54004
----------------	-------	-------

Possible color change:



Abrasion values:	Level:	
Dry	5	53339
Wet	4	
Perspiration	4+	

Permanent folding behavior: 20.000 bucklings	passed	53340
---	--------	-------

Tensile strength: 20 N/mm	passed	53329
------------------------------	--------	-------

Burning behavior: y EN1021 part I u. II	passed	
--	--------	--

Detaillied information about light fastness, abrasion values, skin tollernace and burning behaviour can be found at:  
[www.vegetable-tanned-leather.com/data-and-facts.html](http://www.vegetable-tanned-leather.com/data-and-facts.html)

Tested for  
Heavy metals, aniline  
(Conducted by the German Institute of Environment in Bremen, 2016)



Color: Miss Piggy 226  
Collection: Nappa  
Thickness: 1,4 - 1,6 mm



Optional and only  
subject to availability.  
Please ask explicitly.

# DATA SHEET



## Results of the examination for aniline

Parameter	K 2636 FL-1 Ecopell 226 Miss Piggy KW 40 (mg/kg)	NG (mg/kg)	Requirements IVN Leather (mg/kg)
Aniline	nn	3	≤ 60*

\* Sum limit for further amines going beyond European legislation  
(2,4 Xylidine, N,N. Dimethylaniline, 5-Chlorine-o-toluidine, p-Phenylenediamine and Aniline)

## Results of the examination for heavy metals

Heavy metals	K 2636 FL-1 Ecopell 226 Miss Piggy KW 40 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)
Antimony	<0,5	0,5	1
Aluminium	170	10	500
Arsenic	<0,5	0,5	1
Lead	<0,5	0,5	1
Cadmium	<0,2	0,2	0,2
Chrome	7	1	50
Cobalt	<1	1	5
Mercury	<0,1	0,1	0,2
Nickel	<1	1	5
Titanium	10	10	500
Zirconium	<5	5	500

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected