


DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
Lightfastness:	3	54004
Possible color change:		
Abrasion values:	Level:	
Dry	4 - 5	53339
Wet	4	
Perspiration	4	
Permanent folding behavior: 20.000 bucklings	passed	53340
Tensile strength: 20 N/mm	passed	53329
Burning behavior: EN1021 part I u. II	passed	
Detaillied information about light fastness, abrasion values, skin tollernace and burning behaviour can be found at: www.vegetable-tanned-leather.com/data-and-facts.html		
Tested for Heavy metals, formaldehyde (Conducted by the German Institute of Environment in Bremen, 2013)		

NEMO 626



Color: Nemo 626
Collection: Velour
Thickness: 1,4 - 1,6 mm



Optional and only
subject to availability.
Please ask explicitly.

DATA SHEET



Results of the examination for heavy metals

Heavy metals	H 7899 FL-6 Ecopell 626 Nemo KW 9 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)
Antimony	<0,5	0,5	1
Aluminium	40	10	500
Arsenic	<0,5	0,5	1
Lead	<0,5	0,5	1
Cadmium	<0,2	0,2	0,2
Chrome	8	1	50
Cobalt	<1	1	5
Mercury	<0,1	0,1	0,2
Nickel	<1	1	5
Titanium	<10	10	500
Zirconium	<5	5	500

Results of the examination for formaldehyde

Parameter	H 7899 FL-6 Ecopell 626 Nemo KW 9 (mg/kg)	NG (mg/kg)	Anforderungen IVN Leder (mg/kg)
Methanal (formaldehyde)	nn	1	<50

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected