

DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
------------	--------	----------------

Lightfastness:	4	54004
----------------	---	-------

Possible color change:



Abrasion values:	Level:
------------------	--------

Dry	3	53339
Wet	4	
Perspiration	4 - 5	

Permanent folding behavior: 20.000 bucklings	passed	53340
---	--------	-------

Tensile strength: 20 N/mm	passed	53329
------------------------------	--------	-------

Burning behavior: EN1021 part I u. II	passed
--	--------

Detaillied information about light fastness, abrasion values, skin tollernace and burning behaviour can be found at:
www.vegetable-tanned-leather.com/data-and-facts.html

Tested for
Heavy metals, aniline, PAK
(Conducted by the German Institute of Environment in Bremen, 2013/2015)

OLIFANT 183



Color: Olifant 183
Collection: Velour
Thickness: 1,4 - 1,6 mm



Optional and only
subject to availability.
Please ask explicitly.

DATA SHEET



Results of the examination for aniline

Parameter	K 2407 FL-1 Ecopell 183 Olifant KW 48 (mg/kg)	NG (mg/kg)	Requirements IVN Leather (mg/kg)
Aniline	nn	3	≤ 60*

* Sum limit for further amines going beyond European legislation
(2,4 Xyldine, N,N. Dimethylaniline, 5-Chlorine-o-toluidine, p-Phenylenediamine and Aniline)

Results of the examination for heavy metals

Heavy metals	K 2407 FL-1 Ecopell 183 Olifant KW 48 (mg/kg)	BG (mg/kg)
Antimony	<0,5	0,5
Aluminium	40	10
Arsenic	<1	0,5
Lead	<0,5	0,5
Cadmium	<0,2	0,2
Chrome	10	1
Cobalt	<1	1
Mercury	<0,2	0,1
Nickel	<1	1
Titanium	<10	10
Zirconium	<2	2

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected

DATA SHEET



Results of the examination for PAK

Parameter	H 8094 FL-4 Ecopell 183 Olifant KW 41 (mg/kg)	NG (mg/kg)	Requirements IVN Leather (mg/kg)
Naphthalene	0,13	0,05	–
Acenaphthylene	nn	0,05	–
Acenaphthenes	nn	0,05	–
Fluorene	nn	0,05	–
Phenanthrene	nn	0,05	–
Anthracene	nn	0,05	≤ 0,1
Fluoranthene	nn	0,05	–
Pyrene	nn	0,05	–
Chrysene	nn	0,05	≤ 0,2
Benzo (a) Anthracene	nn	0,05	≤ 0,2
Benzo (b) Fluoranthene	nn	0,05	≤ 0,2
Benzo (k) Fluoranthene	nn	0,05	≤ 0,2
Benzo (a) Pyrene	nn	0,05	≤ 0,2
Indeno (1,2,3-cd) Pyrene	nn	0,05	–
Dibenzo (a, h) Anthracene	nn	0,05	≤ 0,2
Benzo (g, h, i) Perylene	nn	0,05	–
Sum PAK	0,13		≤ 5

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected