

# DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
------------	--------	----------------

PISELLO 219
-------------

Lightfastness:	3-	54004
----------------	----	-------

Possible color change:



Abrasion values:	Level:	
Dry	5	53339
Wet	4 - 5	
Perspiration	4-	

Permanent folding behavior: 20.000 bucklings	passed	53340
---	--------	-------

Tensile strength: 20 N/mm	passed	53329
------------------------------	--------	-------

Burning behavior: y EN1021 part I u. II	passed
--	--------

Detaillied information about light fastness, abrasion values, skin tollernace and burning behaviour can be found at:  
[www.vegetable-tanned-leather.com/data-and-facts.html](http://www.vegetable-tanned-leather.com/data-and-facts.html)

Tested for  
Heavy metals, aniline and p-Phenylendiamin  
(Conducted by the German Institute of Environment in Bremen, 2015/2017)



Color: Pisello 219  
Collection: Nappa  
Thickness: 1,4 - 1,6 mm



Optional and only  
subject to availability.  
Please ask explicitly.

# DATA SHEET



## Results of the examination for heavy metals

Heavy metals	K 1101 FL-2 Ecopell 219 Pisello KW 5 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)
Antimony	<0,5	0,5	1
Aluminium	30	10	500
Arsenic	<0,5	0,5	1
Lead	<0,5	0,5	1
Cadmium	<0,2	0,2	0,2
Chrome	7	1	50
Cobalt	<1	1	5
Mercury	<0,1	0,1	0,2
Nickel	<1	1	5
Titanium	2	10	500
Zirconium	<5	5	500

## Results of the examination for aniline and p-Phenylendiamin

Parameter	K 4659 FL – 5 Ecopell 219 Pisello [mg/kg]	NG (mg/kg)
Aniline	nn	3
p-Phenylendiamin	nn	5

\* Sum limit for further amines going beyond European legislation  
(2,4 Xylidine, N,N. Dimethylaniline, 5-Chlorine-o-toluidine, p-Phenylendiamine and Aniline)

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected