


# DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
Lightfastness:	2 - 3	54004
Possible color change:		
Abrasion values:	Level:	
Dry	4 - 5	53339
Wet	4	
Perspiration	4	
Permanent folding behavior: 20.000 bucklings	passed	53340
Tensile strength: 20 N/mm	passed	53329
Burning behavior: y EN1021 part I u. II	passed	
Detaillied information about light fastness, abrasion values, skin tollernace and burning behaviour can be found at: <a href="http://www.vegetable-tanned-leather.com/data-and-facts.html">www.vegetable-tanned-leather.com/data-and-facts.html</a>		
Tested for Heavy metals, aniline and p-Phenylendiamin (Conducted by the German Institute of Environment in Bremen, 2013/2017)		

TOBAGOBLAU 707



Color: Tobagoblau 707  
Collection: Nappa  
Thickness: 1,4 - 1,6 mm



Optional and only  
subject to availability.  
Please ask explicitly.

# DATA SHEET



## Results of the examination for heavy metals

Heavy metals	H 7899 FL-2 Ecopell 707 Tobagoblau KW 22 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)
Antimony	<0,5	<0,5	<0,5
Aluminium	30	30	30
Arsenic	<0,5	<0,5	<0,5
Lead	<0,5	<0,5	<0,5
Cadmium	<0,2	<0,2	<0,2
Chrome	8	8	8
Cobalt	<1	<1	<1
Mercury	<0,1	<0,1	<0,1
Nickel	<1	<1	<1
Titanium	<10	<10	<10
Zirconium	<5	<5	<5

## Results of the examination for aniline and p-Phenylendiamin

Parameter	K 4659 FL - 1 707 Tobagoblau [mg/kg]	NG (mg/kg)
Aniline	nn	3
p-Phenylendiamin	nn	5

\* Sum limit for further amines going beyond European legislation  
(2,4 Xylidine, N,N. Dimethylaniline, 5-Chlorine-o-toluidine, p-Phenylendiamine and Aniline)

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected