

# DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
Lightfastness:	4+	54004
Abrasion values:	<b>Level:</b>	
Dry	4 - 5	53339
Wet	2	
Perspiration	1	
Permanent folding behavior: 20.000 bucklings	passed	53340
Tensile strength: 20 N/mm	passed	53329

TOPANGA 141



Color: Topanga 141  
Collection: Rodeo PLUS  
Thickness: 2,5 - 2,7 mm

SG-Test: passed

Burning behavior:  
EN1021 part I u. II passed

Detaillied information about light fastness, abrasion values, skin tollernace and burning behaviour can be found at:  
[www.vegetable-tanned-leather.com/data-and-facts.html](http://www.vegetable-tanned-leather.com/data-and-facts.html)

Tested for  
Heavy metals  
(Conducted by the German Institute of Environment in Bremen, 2013)

# DATA SHEET



## Results of the examination for heavy metals

Heavy metals	H 7884 FL-2 Ecopell 141 Topanga KW 31 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)
Antimony	<0,5	0,5	1
Aluminium	30	10	500
Arsenic	<0,5	0,5	1
Lead	<0,5	0,5	1
Cadmium	<0,2	0,2	0,2
Chrome	20	1	50
Cobalt	<1	1	5
Mercury	<0,1	0,1	0,2
Nickel	<1	1	5
Titanium	20	10	500
Zirconium	<5	5	500

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected