


DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
Lightfastness:	4	54004
Possible color change:		
Abrasion values:	Level:	
Dry	4 - 5	53339
Wet	4	
Perspiration	4	
Permanent folding behavior: 20.000 bucklings	passed	53340
Tensile strength: 20 N/mm	passed	53329
Burning behavior: y EN1021 part I u. II	passed	
Detaillied information about light fastness, abrasion values, skin tollernace and burning behaviour can be found at: www.vegetable-tanned-leather.com/data-and-facts.html		
Tested for Heavy metals (Conducted by the German Institute of Environment in Bremen, 2013)		

VALONEA 363



Color: Valonea 363
Collection: Nappa
Thickness: 1,4 - 1,6 mm



Optional and only
subject to availability.
Please ask explicitly.

DATA SHEET



Results of the examination for heavy metals

Heavy metals	G 7991 FL-5 Ecopell 363 Valonea (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)
Antimony	<1	0,5	1
Aluminium	20	10	500
Arsenic	<1	0,5	1
Lead	<1	0,5	1
Cadmium	<0,2	0,2	0,2
Chrome	5	1	50
Cobalt	<1	1	5
Mercury	<0,2	0,1	0,2
Nickel	<1	1	5
Titanium	20	10	500
Zirconium	<5	5	500

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected