

DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
------------	--------	----------------

WALNUSS 166

Lightfastness: 4 54004

Possible color change:



Abrasion values:	Level:	
Dry	3 - 5	53339
Wet	4 - 5	
Perspiration	4 - 5	

Permanent folding behavior:
20.000 bucklings passed 53340

Tensile strength:
20 N/mm passed 53329

Burning behavior:
EN1021 part I u. II passed

Detailed information about light fastness, abrasion values, skin tolerance and burning behaviour can be found at:
www.vegetable-tanned-leather.com/data-and-facts.html

Tested for
Heavy metals, aniline
(Conducted by the German Institute of Environment in Bremen, 2013/2014)



Color: Walnuss 16
Color-lection: Velour
Thickness: 1,4 - 1,6 mm



Optional and only
subject to availability.
Please ask explicitly.

DATA SHEET



Results of the examination for aniline

Parameter	H 8235 FL-4 Ecopell 166 Walnuss KW 45 (mg/kg)	NG (mg/kg)	Requirements IVN Leather (mg/kg)
Aniline	nn	5	60*

* Sum limit for further amines going beyond European legislation
(2,4 Xylidine, N,N. Dimethylaniline, 5-Chlorine-o-toluidine, p-Phenylenediamine and Aniline)

Results of the examination for heavy metals

Heavy metals	H 8235 FL-4 Ecopell 166 Walnuss KW 45 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)
Antimony	<0,5	0,5	1
Aluminium	5.300	10	500
Arsenic	<0,5	0,5	1
Lead	<0,5	0,5	1
Cadmium	<0,2	0,2	0,2
Chrome	8	1	50
Cobalt	<1	1	5
Mercury	<0,1	0,1	0,2
Nickel	<1	1	5
Titanium	<10	10	500
Zirconium	<5	5	500

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected