

DATA SHEET




TESTED FOR	RESULT	CONFIRM TO DIN
------------	--------	----------------

HIPPO 362

Lightfastness:	1 - 2	54004
----------------	-------	-------

Possible color change:



Abrasion values:	Level:	
Dry	5	
Wet	4 - 5	53339
Perspiration	4 - 5	


Permanent folding behavior: 20.000 bucklings	passed	53340
---	--------	-------

Tensile strength: 20 N/mm	passed	53329
------------------------------	--------	-------

Burning behavior: y EN1021 part I u. II	passed
--	--------

Detaillied information about light fastness, abrasion values, skin tollernace and burning behaviour can be found at:
www.vegetable-tanned-leather.com/data-and-facts.html

Tested for
Heavy metals, aniline
(Conducted by the German Institute of Environment in Bremen, 2013/2014)



Color: Hippo 362
Collection: Nappa
Thickness: 1,4 - 1,6 mm