

DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
------------	--------	----------------

PURPUR 224

Lightfastness:	1 - 2	54004
----------------	-------	-------

Possible color change:



Abrasion values:	Level:	
Dry	5	53339
Wet	4-	
Perspiration	4+	

Permanent folding behavior: 20.000 bucklings	passed	53340
---	--------	-------

Tensile strength: 20 N/mm	passed	53329
------------------------------	--------	-------

Burning behavior: y EN1021 part I u. II	passed
--	--------

Detaillied information about light fastness, abrasion values, skin tollernace and burning behaviour can be found at:
www.vegetable-tanned-leather.com/data-and-facts.html

Tested for
Heavy metals, aniline and p-Phenylendiamin
(Conducted by the German Institute of Environment in Bremen, 2013/2017)



Color: Purpur 224
Collection: Nappa
Thickness: 1,4 - 1,6 mm

DATA SHEET



Results of the examination for heavy metals

Heavy metals	H 8168 FL-5 Ecopell 224 Purpur KW 43 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)
Antimony	<0,5	0,5	1
Aluminium	40	10	500
Arsenic	<0,5	0,5	1
Lead	<0,5	0,5	1
Cadmium	<0,2	0,2	0,2
Chrome	11	1	50
Cobalt	<1	1	5
Mercury	<0,1	0,1	0,2
Nickel	<1	1	5
Titanium	<10	10	500
Zirconium	<5	5	500

Results of the examination for aniline and p-Phenylendiamin

Parameter	K 4659 FL – 3 Ecopell 224 Purpur [mg/kg]	NG (mg/kg)
Aniline	nn	3
p-Phenylendiamin	nn	5

* Sum limit for further amines going beyond European legislation
(2,4 Xylidine, N,N. Dimethylaniline, 5-Chlorine-o-toluidine, p-Phenylenediamine and Aniline)

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected